

טבלת השוואת תוצאות הבדיקה

N%	Frequency, Hz	מלמין ללא צבע (טבעי)			מלמין צבוע		
		Random Sound incidence absorption α_s	Practical Sound absorption coefficient α_p	Weighted absorption coefficient α_w	Random Sound incidence absorption α_s	Practical Sound absorption coefficient α_p	Weighted absorption coefficient α_w
1	100	0.10			0.12		
2	125	0.20	0.20		0.21	0.20	
3	160	0.25			0.28		
4	200	0.31			0.33		
5	250	0.44	0.45		0.45	0.45	
6	315	0.56			0.59		
7	400	0.77			0.82		
8	500	0.86	0.85		0.88	0.90	
9	630	0.99			1.02		
10	800	1.00			1.03		
11	1000	1.02	1.00	0.70(MH)	0.99	1.00	0.70(MH)
12	1250	0.96			0.98		
13	1600	1.00			1.01		
14	2000	0.98	1.00		0.97	1.00	
15	2500	0.97			0.99		
16	3150	1.00			1.02		
17	4000	1.01	1.00		1.00	1.00	
18	5000	1.04			1.00		

אין הבדל בין התוצאות הבדיקות, כל ההבדלים הקטנים במסגרת אי-וודאות של הבדיקה.

